

## **AQUA 20**20mil Reinforced Polyethylene

## SPECIFICATION SHEET

Heavyweight fabric incorporating a special weave pattern to enhance thickness, flatness, and tear properties. For use in <u>geomembrane applications</u> such as soil remediation, <u>pond lining</u>, <u>canal lining</u>, <u>landfill covers</u>, etc.

## PRODUCT SPECIFICATIONS

WEAVE	Woven black HDPE scrim		
COATING	2.5 mil average each side		
COLOR	Black or other colored coatings available		
WEIGHT	9.6 oz/yd² +/- 5%		
THICKNESS	XNESS 20mils +/- 10% ASTM D1777		

## PRODUCT PERFORMANCE

GRAB TENSILE	Warp 330 lb	Weft 286 lb	ASTM D751
STRIP TENSILE	Warp 235 lb	Weft 147 lb	ASTM D751
TRAPEZOIDAL TEAR	Warp 110 lb	Weft 92 lb	ASTM D4533
MULLEN BURST	600 psi		ASTM 751
HYDROSTATIC RESISTANCE	352 psi		ASTM D751
MOISTURE VAPOR TRANSMISSION	0.47 g/m <sup>2</sup> /24 hours (0.07 perms)		ASTM E96, pr. B
PERMEABILITY	<1.3 x 10 <sup>-7</sup> cm/sec		ASTM D4491
PUNCTURE RESISTANCE INDEX	171 lb		ASTM D4833
ACCELERATED UV WEATHERING	>90% strength retention after		
ACCELERATED OF WEATHERING	2000 hours exposure @0.77 W/m <sup>2</sup> /nm or 1200		ASTM G150-00
	hours exposure @ 1.35 W/m <sup>2</sup> /nm		ASTM G154-04

 $<sup>^1\</sup>text{Q.U.V}$  [A-340 Lamps]: 8 hrs UV @ 60°C; 4 hrs condensation @ 50°C

All information, recommendations and suggestions appearing in this literature concerning the use of our products are based upon test and data believed to be reliable; however, it is the user's responsibility to determine the suitability for their own use of the products described herein. Since the actual use by others is beyond our control, no guarantee or warranty of any kind, expressed or implied, is made by Carson MFG. as to the effects of such use or the results to be obtained, nor does Carson MFG. assume any liability in connection herewith. Any Statement made herein may not be absolutely complete since additional information may be necessary or desirable when particular or exceptional conditions or circumstances exist or because of applicable laws or government regulations. Nothing herein contained is to be construed as permission or as a recommendation to infringe any patent.