



AQUA 30

30mil Reinforced Polyethylene

SPECIFICATION SHEET

Heavyweight fabric incorporating a special weave pattern to enhance thickness, flatness, and tear properties. The coating recipe is designed to improve abrasion resistance. For use in [geomembrane applications](#) such as soil remediation, [pond lining](#), [canal lining](#), [landfill covers](#), etc.

PRODUCT SPECIFICATIONS

WEAVE	Woven black HDPE scrim
COATING	3.0 mil average each side
COLOR	Black
WEIGHT	13.4 oz/yd ² (454 g/m ²) +/- 5%
THICKNESS	Nominal 30 mil (0.75 mm) +/- 10% ASTM D1777

PRODUCT PERFORMANCE

GRAB TENSILE	Warp 375 lb 1668 N	Weft 315 lb 1401 N	ASTM D751
TOUNGE TEAR	Warp 270 lb 1201 N	Weft 225 lb 1000N	ASTM D751
TRAPEZOIDAL TEAR	Warp 100 lb 444 N	Weft 90 lb 400 N	ASTM D4533-04
MULLEN BURST	720 psi 4966 kPa		ASTM D751
HYDROSTATIC RESISTANCE	610 psi 4196 kPa		ASTM D751-00
PERMEABILITY	<1.3 x 10 ⁻⁹ cm/sec		ASTM D4491-99a
PUNCTURE RESISTANCE INDEX	225 lb 1000 N		ASTM D4833-00
ACCELERATED UV WEATHERING ¹	>90% strength retention after 2000 hours exposure @0.77 W/m ² /nm or 1200 hours exposure @ 1.35 W/m ² /nm		ASTM G150-00 ASTM G154-04

¹Q.U.V [A-340 Lamps]: 8 hrs UV @ 60°C; 4 hrs condensation @ 50°C

All information, recommendations and suggestions appearing in this literature concerning the use of our products are based upon test and data believed to be reliable; however, it is the user's responsibility to determine the suitability for their own use of the products described herein. Since the actual use by others is beyond our control, no guarantee or warranty of any kind, expressed or implied, is made by Carson MFG. as to the effects of such use or the results to be obtained, nor does Carson MFG. assume any liability in connection herewith. Any Statement made herein may not be absolutely complete since additional information may be necessary or desirable when particular or exceptional conditions or circumstances exist or because of applicable laws or government regulations. Nothing herein contained is to be construed as permission or as a recommendation to infringe any patent.